

PROPERTIES MC-OIL

Legend

★ : values referring to dry material

★★ : values referring to material in equilibrium with the standad atmosphere 23°C/50% RH(mostly derived from literature)

► This table is available help in the choice of a material. The data listed here fall with in the normal range of product properties.

However, they are not guaranteed and they should not beused to establish material specification limits nor used alone as the basis of design

PROPERTIES	ITEM		Method	Unit	MC-OIL	
			ISO/(IEC)			
	Color		-	-	yellow	
	Density		1183	g/cm ³	1.11	
	Water absorption	After 24/96h immersion in water of 23°C At saturation air 23°C, 50%RH At saturation in water of 23°C	62	mg	-/-	
			62	%	0.5/-	
			-	%	-	
-			%	6.3		
Thermal Properties	Melting Temperature		-	°C	220	
	Thermal conductivity at 23°C		-	W/(K·m)	-	
	Coefficient of inear Thermal expansion	Average value btw23~60°C	-	m/(m ·K)	-	
		Average value btw23~100°C	-	m/(m ·K)	90 · 10 ⁻⁶	
	Temperature of Deflection under load	Method A : 1.8Mpa ★	75	°C	115	
	Max. allowable Service temp. in air	For short periods Continously : 5,000/20,000h	-	°C	-	
			-	°C	-/-	
Min.service temperature		-	°C	-		
Flammability	UL94 (3/6mm thickness)	-	-	HB/HB		
Mechanical Properties at 23°C	Tension test	Tensile stress ★	527	MPa	68	
		★★	527	MPa	-	
		Tensile strainat break ★	527	%	14	
		★★	527	%	-	
		Tensile modulus of elasticity ★	527	Mpa	3000	
	★★	527	MPa	-		
	Compression test	Compressive stress at 1/2/5/% nominal strain ★	604	MPa	-/-/75	
	Izod impact strength-Notched		★	180/2A	kJ/m ²	3.9
			★★	180/2A	kJ/m ²	-
	Rockwell hardness		★	2039-2	-	R110
Electrical Properties at 23°C	Electric strength		★	(60243)	KV/mm	-
			★★	(60243)	KV/mm	-
	Volume resistivity		★	(60093)	Ω·cm	>10 ¹⁴
			★★	(60093)	Ω·cm	-
	Surface resistivity		★	(60093)	Ω	>10 ¹³
			★★	(60093)	Ω	-
	Relative permittivity:	100Hz	★	(60250)	-	-
			★★	(60250)	-	-
		1MHz	★	(60250)	-	-
			★★	(60250)	-	-
	Dielectric dissipation factor:	100Hz	★	(60250)	-	-
			★★	(60250)	-	-
		1MHz	★	(60250)	-	-
			★★	(60250)	-	-
Comparative tracking index(CTI)		★	(60112)	-	-	
		★★	(60112)	-	-	